



# White / Grey PROTHERM<sup>®</sup> LIGHT

**LIGHTWEIGHT PLASTER  
FOR THE PASSIVE FIRE PROTECTION**

## PROTHERM LIGHT<sup>®</sup> - White and Grey Lightweight plaster for the passive fire protection

PRODUCT	Lightweight premixed thermal insulating plaster for fire protection (REI) of masonry structure, reinforced concrete, concrete and steel structures, made of virgin EPS beads, water binders and special additives. To be mixed with water during the application. <b>Available white and grey.</b>	
FIELDS OF APPLICATION	<ul style="list-style-type: none"> <li>Fireproofing protective system, specific to improve fire resistance of structural elements made of steel, brick, normal and pre-stressed reinforced concrete and on buildings for civil and industrial uses.</li> <li>Mechanical application.</li> <li>For indoor and outdoor use.</li> </ul>	
CHARACTERISTICS	Density:	~ 18.73 lb/ft <sup>3</sup>
	Drying:	On surface: 24 hours, at 68 °F with natural ventilation
	Chemical characteristic:	Rotproof and inert material, high breathability and waterproofing properties, very good resistance to weather agents
	Physical characteristics:	Very good characteristics of mechanical resistance, high thermal insulating and acoustic properties
	Fire reactivity:	A1 (UNI EN 13501-1)
	Compressive strength:	141 psi (according with UNI EN ISO 12390-3)
	Flexural strength:	51 psi (according with UNI EN ISO 12390-5)
	Thermal conductivity [K-Value]:	0,079 W/mK (UNI EN 12667)
	Factor of resistance to water vapour diffusion μ:	9 (UNI EN 1015-19)
OMOLOGATIONS AND CERTIFICATIONS	The tests performed on the product, in accordance with UNI ENV 13381 Regulation, have obtained the following classification reports. This is the only main tool for the dimensioning of the product's thickness, necessary to guarantee the fire resistance class required.	
	APPLICATION	REGULATION
	Reinforced concrete	UNI ENV 13381-3
	Steel	UNI ENV 13381-4
	Composite slabs profiled sheet + Concrete	UNI ENV 13381-5
	ASSESSMENT REPORT	
		CSI1895FR - CSI1896FR CSI1784FR 13_02603-1-a
CONSUMPTION / YIELD	~ 0.6 lb/ft <sup>2</sup> for 3/8" of thickness. Each bag ~ 65 ft <sup>2</sup> for 3/8" of thickness.	



Protherm light Fireproofing Division



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy  
Ph. +39 0535 82161 . Fax +39 0535 82970 . [www.edilteco.com](http://www.edilteco.com) | [info@edilteco.com](mailto:info@edilteco.com)

© Copyright EDILTECO S.p.A. - Non authorized reproduction is forbidden.

COMPANY WITH  
QUALITY SYSTEM  
CERTIFIED BY DNV GL  
= ISO 9001 =

PACKAGING AND STORAGE	<ul style="list-style-type: none"> <li>· Bag of 39.7 lb.</li> <li>· Pallet (protected by thermo-wrapping film): n° 40 bags = 1,587.3 lb.</li> <li>· It is recommended the use within 6 months from the packaging. The product maintains the technical characteristics for over 12 months if conveniently stored (in a dry and fresh place, protected from frozen, water and direct sunlight). It is recommended to use suitable protection devices.</li> </ul>
SUPPORT PREPARATION	The preparation must be suitable to guarantee a support complies to what reported in the classification report inherent to the type of element on which will be applied.
APPLICATION	Mechanical application, using a sprayer, with suitable plastering machine (type PFTG4, G5 or similar, always opportunely equipped), with one or more coats, according to the thickness to be realized. The surfaces to be treated must be coated without interruption of continuity, with the prescribed thickness. To improve the covering drying, we recommend to work in well-ventilated places and with ambient and support temperatures of at least 41 °F and not over 95 °F. For thicknesses less than 13/16", the product application can be realized with an unique application; for thicknesses over 13/16" are necessary more applications, according to the total thickness. <i>For more detailed information, consult the Application manual or contact our Technical Department.</i>
WARNINGS	<ul style="list-style-type: none"> <li>· Do not apply under the direct sunlight and rain. Apply with temperatures between 41 °F and 95 °F.</li> <li>· Do not apply if there is risk of frost.</li> <li>· Do not mix with any other products.</li> <li>· Equipments cleaning: with water, immediately after use.</li> </ul>

All the indications provided in this technical data sheet are purely approximate and not binding for legal purpose. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on building sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installation. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all methods and instructions for use generally referable to "workmanlike" execution. Edilteco S.p.A. reserves the right to change the contents of this mechanical data sheet on its final judgements. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.



Protherm light Fireproofing Division

DS PROTHERM LIGHT . Rev 12/2018 . USA



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy  
Ph. +39 0535 82161 . Fax +39 0535 82970 . [www.edilteco.com](http://www.edilteco.com) | [info@edilteco.com](mailto:info@edilteco.com)

COMPANY WITH  
QUALITY SYSTEM  
CERTIFIED BY DNV GL  
= ISO 9001 =

© Copyright EDILTECO S.p.A. - Non authorized reproduction is forbidden.